



---

# BRUGSE ABDIJMOEF®

---

## DESCRIPTION FORM

The visible brickwork will be carried out in non-perforated moulded facing brick made of pure clay, which is treated according to a process developed in house that gives the facing bricks the appearance of recovery bricks. Sometimes, quarter, half, and three-quarter bricks are in the packs, owing to the tumble process. The colour is predominantly yellow with shades of grey-yellow. The bricks are suited for every building style and have the necessary properties required of contemporary facing bricks. In order to protect and guarantee their authenticity, the bricks are registered.



## COMPOSED AFTER CE-COMPLIANT FACING BRICKS WITH THE FOLLOWING CHARACTERISTICS

Type	Facing brick with a traditional appearance
Colour	predominantly yellow with shades of grey-yellow
Format (mm)	EF 217/102/65
Number per m <sup>2</sup> (*)	55
Recommended masonry (**)	Random pattern
Number per pack / weight per pack (kg)	550/1080
Common brick category	I-HD
Size tolerance	T2
Class row	R1
Fire reaction / Euroclass	A1
Soluble salt content	S2
Efflorescence	no efflorescence
Durability / frost resistance	F2 highly frost resistant
Porosity (%)	<= 24
Average compressive strength (N/mm <sup>2</sup> )	>= 15
Thermal conductivity (W/mK)	0,37

(\*) Depending on the layer size used

(\*\*) see also our installation method

### REMARK

The presented values and colours are only approximtee. To obtain the same colour overall in the brickwork, the bricks from different packs must be mixed together. The complete part of bricks must be delivered at once. Clay bricks may show some slight colour variation per production batch from previous batches. The manufacturer reserves the right to change the product range and the packaging.